

Widerstandsmoment $W \text{ cm}^3$ für Stahlrohre bis 9,5 mm Wandstärke

Ø	Wandstärke in mm										
	3.6	4.0	4.5	5.0	5.6	5.9	6.3	7.1	8.0	8.8	9.5
48.3	5.3	5.7	6.2	6.7	7.2	7.5	7.8	8.3	8.8	9.3	9.6
60.3	8.6	9.3	10.2	11.1	12.1	12.5	13.1	14.2	15.2	16.1	16.8
70	11.9	12.9	14.2	15.5	16.9	17.6	18.4	20.1	21.7	23.1	24.2
73	13.0	14.2	15.6	17.0	18.6	19.3	20.3	22.1	24.0	25.5	26.7
76.1	14.2	15.5	17.1	18.6	20.4	21.2	22.3	24.3	26.4	28.1	29.5
82.5	16.9	18.5	20.4	22.2	24.4	25.4	26.7	29.2	31.8	34.0	35.8
88.9	19.8	21.7	24.0	26.2	28.7	29.9	31.5	34.6	37.8	40.4	42.6
95	22.7	25.0	27.6	30.2	33.2	34.6	36.5	40.1	43.9	47.1	49.7
101.6	26.2	28.8	31.9	34.9	38.4	40.1	42.3	46.6	51.1	54.8	57.9
108	29.8	32.8	36.3	39.8	43.8	45.8	48.3	53.3	58.5	62.9	66.6
114.3	33.6	36.9	41.0	44.9	49.5	51.8	54.7	60.3	66.4	71.5	75.7
121	37.8	41.6	46.2	50.7	56.0	58.5	61.9	68.3	75.3	81.1	86.1
127	41.8	46.1	51.2	56.2	62.1	64.9	68.7	75.9	83.7	90.3	95.9
133	46.1	50.7	56.4	62.0	68.5	71.7	75.8	83.9	92.6	100.0	106.2
139.7	51.0	56.2	62.6	69.8	76.0	79.6	84.2	93.3	103.1	111.4	118.4
152.4	61.1	67.4	75.1	82.6	91.4	95.7	101.4	112.4	124.4	134.7	143.4
159	66.7	73.6	82.0	90.2	99.9	104.7	110.9	123.1	136.4	147.7	157.3
168.3	75.1	82.8	92.3	101.6	112.6	118.0	125.1	139.0	154.1	167.1	178.1
177.8	84.1	92.8	103.5	114.0	126.4	132.5	140.5	156.2	173.3	188.0	200.6
193.7	100.3	110.7	123.6	136.2	151.2	158.5	168.2	187.2	208.0	225.9	241.2
219.1	129.1	142.7	159.4	175.9	195.4	205.0	217.7	242.6	270.0	293.7	314.0
244.5		178.7	199.8	220.6	245.3	257.5	273.6	305.3	340.1	370.5	396.5
273		223.9	250.5	276.8	308.0	323.4	343.8	384.1	428.5	467.1	500.4
298.5		268.7	300.8	332.5	370.2	388.8	413.5	426.3	516.1	563.2	603.7
323.9		317.4	355.4	393.1	437.8	460.0	489.3	547.4	611.6	667.7	716.2
339.7				433.3	482.7	507.2	539.7	603.9	675.0	737.3	791.0
355.6				475.8	530.1	557.1	592.9	663.6	742.1	810.7	870.0
406.4				624.7	696.5	732.2	779.6	873.3	978.0	1069	1148
457.2				793.9	885.6	931.2	991.8	1112	1245	1363	1464
508				983.3	1097	1154	1229	1379	1546	1692	1819
Ø	3.6	4.0	4.5	5.0	5.6	5.9	6.3	7.1	8.0	8.8	9.5

Widerstandsmoment $W \text{ cm}^3$ für Stahlrohre ab 10.0 mm Wandstärke

Ø	Wandstärke in mm									
	10.0	11.0	12.5	14.2	16.0	17.5	20.0	22.2	25.0	30.0
48.3	9.8	10.1	10.5							
60.3	17.2	18.0	19.0	19.8	20.5					
70	24.9	26.2	27.9	29.5	30.7	31.6	32.5			
73	27.6	29.1	31.0	32.9	34.4	35.4	36.6			
76.1	30.5	32.2	34.5	36.6	38.4	39.6	41.1			
82.5	36.9	39.2	42.1	44.9	47.4	49.0	51.2	52.6	53.8	
88.9	44.1	46.8	50.5	54.2	57.4	59.6	62.6	64.6	66.4	
95	51.4	54.8	59.3	63.8	67.9	70.7	74.7	77.4	79.9	
101.6	60.1	64.1	69.7	75.2	80.2	83.9	89.0	92.6	96.1	100.0
108	69.1	73.9	80.5	87.1	93.3	97.8	104.2	108.7	113.3	118.8
114.3	78.6	84.2	91.9	99.8	107.1	112.6	120.4	126.0	131.8	139.1
121	89.4	95.9	105.0	114.2	122.9	129.5	138.9	145.9	153.2	162.6
127	99.7	107.1	117.4	128.0	138.1	145.6	156.7	165.0	173.8	185.4
133	110.6	118.8	130.5	142.5	154.1	162.8	175.7	185.4	195.8	209.9
139.7	123.3	132.7	145.9	159.7	173.0	183.1	198.1	209.6	222.0	239.0
152.4	149.5	161.1	177.7	195.1	212.0	225.0	244.5	259.7	277.0	300.0
159	164.0	177.0	195.4	214.9	233.9	248.5	270.7	288.0	307.0	335.0
168.3	185.8	200.7	221.9	244.4	266.5	283.7	309.8	330.0	354.0	388.0
177.8	209.3	226.4	250.7	276.6	302.1	322.0	352.5	377.0	404.0	445.0
193.7	252.0	272.8	302.8	334.9	366.8	391.8	430.0	461.0	497.0	551.0
21.91	328.3	356.1	396.4	439.7	483.0	518.0	571.0	615.0	666.0	745.0
244.5	414.7	450.5	502.6	559.0	616.0	661.0	732.0	791.0	860.0	969.0
273	523.8	569.8	637.0	710.0	784.0	843.0	937.0	1015	1108	1257
298.5	632.2	688.4	770.0	860.0	952.0	1025	1142.	1239	1356	1546
323.9	750.3	818.0	916.0	1024	1135	1224	1366	1485	1629	1865
339.7	829.0	904.0	1013	1134	1257	1357	1516	1650	1812	2079
355.6	912.0	995.0	1116	1249	1386	1497	1675	1824	2005	2305
406.4	1204	1314	1477	1657	1842	1992	2235	2440	2691	3110
457.2	1536	1679	1889	2122	2362	2558	2876	3146	3477	4035
508	1909	2088	2351	2644	2948	3195	3598	3941	4364	5083
Ø	10.0	11.0	12.5	14.2	16.0	17.5	20.0	22.2	25.0	30.0